

ARMOURFLOW™

PANEL DRAIN

TECHNICAL DATA SHEET	TDS G 001 032
ISSUE NUMBER	03
DATE	SEPTEMBER 2020

CHARACTERISTICS	STANDARD	NOMINAL VALUE	UNIT	TOLERANCE
GEOSPACER: NO SENSITIVE TO WATER				
POLYMER	-	HPPE	-	-
STRUCTURE	-	Alveolar, thermoformed, isotropic and symmetric	-	-
THICKNESS UNDER 2kPa	EN ISO 9863-1 ASTM D-5199	12	mm	±10%
CRUSH RESISTANCE	EN ISO 25619-2 ASTM D-6364	275 5743	kPa psf	-10% -10%
COMPRESSIVE CREEP UNDER 100kPa/10 Years	EN ISO 25619-1	-9% of the thickness under stress		
GEOTEXTILE: NO SENSITIVE TO WATER				
PRODUCT REFERENCE	-	D100		
CERTIFICATE ASQUAL	-	Uncertified		
POLYMER	-	Polypropylene		
MANUFACTURING PROCESS	-	Non woven thermally bonded		
POSITION OF THE GEOTEXTILE ON THE GEOSPACER	-	A geotextile on a face		
THICKNESS UNDER 2kPa	EN ISO 9863-1 ASTM D-5199	0,41	mm	±0,08
MASS PER UNIT AREA	EN ISO 9864 ASTM D-5161	100	g/m ²	±10
OPENING SIZE O90w	EN ISO 12956	150	µm	±30
WATER PERMEABILITY VH50	EN ISO 11058	0,08	m/s	-0,015
GEOCOMPOSITE				
DYNAMIC PERFORATION RESISTANCE	EN ISO 13433	40	mm	+7
WATER FLOW CAPACITY IN THE PLANE/TRANSMISSIVITY	EN ISO 12958 ASTM D-4716	Foam/Obturate i=1; 20kPa; 11,2x10 ⁻⁴	m ² /s	-2,3 x 10 ⁻⁴
TENSILE STRENGTH	EN ISO 10319 ASTM D-4595	MD: 18 CMD: 18	kN/m	-2,34 -2,34
DURABILITY IN ACCORDANCE WITH ANNEX B	To be covered within 2 weeks after installation. Predicted to be durable for more than 50 years in all natural soils with temperatures <25°C on the basis of a durability assesment (Typargeo Report 070)			
ADDITIONAL DATA ON THE GEOCOMPOSITE				
MASS PER UNIT	EN ISO 9864 ASTM D-5161	1051	g/m ²	±10%
DIMENSIONS				
GEOSPACER WIDTH	1,1 m			
GEOTEXTILE WIDTH	1,2 m			
LENGTH	25m			

DISCLAIMER

The information provided in this publication is correct to the best knowledge of the company and is given out in good faith. The information presented herein is intended only as a general guide to the use of such products and no liability is accepted by Cirtex Industries Ltd for any loss or damage however arising, which results either directly or indirectly from the use of such information. Cirtex Industries Ltd has a policy of continuous development so information and product specifications may change without notice.