Pozidrain 4S250D/NW8

Data Sheet

POZIDRAIN 4S250D/NW8 is a geocomposite drainage layer comprising a high performance single cuspated HDPE core with a geotextile filter thermally bonded on the dimple side and a friction geotextile thermally bonded on the flat side. The textile filter has a flap extending beyond the core on one edge.
The major application is for use as a drainage layer particularly on steep slopes in environmental containment.

Geocomposite Properties				
Thickness at 2kPa [4]	(mm)	5.5	nominal	EN ISO 9863-1
Mass per unit area [4]	(g/m²)	760	nominal	EN ISO 9864
Tensile strength MD / CMD [4]	(kN/m)	19.0 / 19.0	-13%	EN ISO 10319
Elongation at break MD / CMD [4]	(%)	40 / 50	nominal	EN ISO 10319
CBR puncture resistance [4]	(N)	3 700	-20%	EN ISO 12236
Short term compressive strength	Sufficient for installation pressure < 500kPa			
Compressive creep at 114 years at 20kPa (extrapolated 10,000 hours)	(%)	≤ 5	nominal	EN ISO 25619-1
Compressive creep at 114 years at 250kPa	(%)	≤ 25	nominal	ASTM D7361
Perpendicular Water Inflow				
Water flow at 50mm head	(l/m².s)	101	±30%	EN ISO 11058
At 2kPa permeability *(coefficient)*	(m/s)	2.6×10^{-3}	±30%	EN ISO 11058
Breakthrough head	(mm)	0	nominal	
In-plane water flow MD [6]		**HG = 1.0**	**HG = 0.1**	
20kPa	(l/m.s)	0.85 -0.15	0.25 -0.07	EN ISO 12958
100kPa	(l/m.s)	0.65 -0.15	0.20 -0.05	EN ISO 12958
200kPa	(l/m.s)	0.55 -0.10	0.15 -0.05	EN ISO 12958
Tested with **sott foam** contact surfaces to simulate textile intrusion into the core due to soil pressure. Hard platen interfaces are not representative of product performance as installed. Suitable for long term 114 year confining pressures up to 250kPa. [5]				
Geotextile Properties				
Thickness at 2kPa [4]	(mm)	1.2	nominal	EN ISO 9863-1
Tensile strength MD / CMD [4]	(kN/m)	9.5 / 9.5	-13%	EN ISO 10319
CBR puncture resistance [4]	(N)	1 600	-20%	EN ISO 12236
Dynamic perforation cone drop [4]	(mm)	29	+25%	EN ISO 13433
Pore size O_{90}	(µm)	120	±30%	EN ISO 12956
Type and material	Nonwoven needle-punched and heat-treated long staple fibre polypropylene.			
Durability				
Resistance to UV – Strength retained 50MJ/m²	(%)	> 60		EN 12224
Resistance to chemicals – Strength retained 3 ≤ pH ≤ 12	(%)	> 90		EN 14030
Design life	100 years in natural soils with 4 ≤ pH ≤ 9 and soil temperatures ≤ 25°C on the basis of the results of test method B.4.2.2 (112 days) of EN 13252:2016 Annex B.			
Product Dimensions				
Product dimensions [3]	Euroliner 4.4m x 110m. Other sizes on request. Container 5.5m x 110m. Other sizes on request. Roll diameter approx. 820mm. Tube ID 100mm.			

1 The values given are determined from statistical Interpretation of test results obtained in our laboratories and are subject to tolerances. In line with our policy of continuous improvement the right is reserved to make changes without notice at any time.
2 Final determination of the suitability of any information is the sole responsibility of the user. ABG will be pleased to discuss the use of this or any other product but responsibility for selection of a material and its application in any specific project remains with the user.
3 The tolerance on roll length is ±1.5% and on roll width is ±1.0%; in multi-core products this may manifest itself between core elements.
4 Thickness, Mass, CBR, Dynamic perforation cone drop and Tensile strength are given only to enable rapid CQA checks.
5 Guidance on interface shear strength, creep, reduction factors and certain other parameters is available. Site specific tests are strongly recommended.
6 CMD flow is typically 80% of the value in the MD.

Distributed nationwide in ANZ by Cirtex
CIRTEX® GAIN MORE GROUND

Level 1 - 1 Westlink Court,
Darra QLD 4076, Australia
Phone: 1800 012 681
Mail: info@cirtex.com.au

125 Ngati Maru Highway,
Thames 3578, New Zealand
Phone: 0800 247 839
Mail: info@cirtex.co.nz