

ECC3™

High Performance Turf Reinforcement Matting

TECHNICAL DATA SHEET	TDS G 001 146
ISSUE NUMBER	02
DATE	NOVEMBER 2019

ECC3 is made with a matrix of UV stabilised Polypropylene meshes filled with a uniformly distributed 100% coconut fibre to assist with vegetation establishment. ECC3 is a permanent turf reinforcement mat and is suitable for 1:1 slopes and high-flow channels.

PROPERTY	TEST METHOD	TEST VALUE	
PHYSICAL			
Roll Size		2.4 m x 34.3 m	
Mass/Unit Area	ASTM D-6566	449.2 g/m ²	
Thickness	ASTM D-6525	8.64 mm	
Light Penetration (% Passing)	ASTM D-6567	14%	
Colour	Visual - Netting	Black	
	Visual - Matting	Brown	
MECHANICAL			
Tensile Strength MD/TD	ASTM D-6818	11.70 kN/m / 9.38kN/m	
Elongation MD/TD	ASTM D-6818	25% / 15%	
ENDURANCE			
UV Resistance @ 1000 hours	ASTM D-4355	98%	
SLOPE PERFORMANCE DESIGN VALUES*			
C-FACTORS	ASTM D-6459	0.00	
SLOPE LENGTH (L)	≤ 3:1	3:1 - 2:1	≥ 2:1
< 15m	0.001	0.007	0.047
15m - 30m	0.008	0.015	0.069
> 30m	0.027	0.050	0.089
CHANNEL PERFORMANCE DESIGN VALUES*			
Unvegetated Shear Stress	ASTM D-6460	153.22 Pa	
Unvegetated Velocity	ASTM D-6460	3.51 m/s	
Vegetated Shear Stress	ASTM D-6460	574.56 Pa	
Vegetated Velocity	ASTM D-6460	7.62 m/s	
Manning's N		0.024	



ISO 9001:2015
Reg.No: C41186

*Large Scale Results obtained by a 3rd Party GAI Accredited Independent Laboratory.

The listed typical values are guiding values, achieved in our laboratories and/or independent testing institutes.

DISCLAIMER: All information provided in this publication is correct to the best knowledge of the company and is given out in good faith. The information presented herein is intended only as a general guide to the use of such products and no liability is accepted by Cirtex Industries Ltd for any loss or damage however arising, which results either directly or indirectly from the use of such information. Cirtex Industries Ltd has a policy of continuous development so information and product specifications may change without notice.

