

# TERRATEX® - K SERIES

## HEAVYWEIGHT NEEDLE PUNCHED NON-WOVEN GEOTEXTILES

|                     |                |
|---------------------|----------------|
| TECHNICAL DATASHEET | G 030 003      |
| ISSUE NUMBER        | 01             |
| DATE                | SEPTEMBER 2019 |

| PROPERTY   |         | TEST METHOD   | UNIT                  | 750K      | 920K      | 1300K     | 1850K     |
|--|---------|---------------|-----------------------|-----------|-----------|-----------|-----------|
| STRENGTH PROPERTIES  |         | -             | -                     | MC/CD     | MC/CD     | MC/CD     | MC/CD     |
| Wide Strip Tensile Strength  | Typical | AS 3706.2     | kN/m                  | 38/38     | 47/47     | 65/65     | 85/85     |
|  | MARV    | AS 3706.2     | kN/m                  | 33/33     | 40/40     | 56/56     | 73/73     |
| Grab Tensile Strength  | Typical | AS 2001.2.3.2 | N                     | 2350/2350 | 2750/2750 | 4150/4150 | 5000/5000 |
|  | MARV    | AS 2001.2.3.2 | N                     | 2000/2000 | 2350/2350 | 3550/3550 | 4250/4250 |
| Trapezoidal Tear Strength  | Typical | AS 3706.3     | N                     | 920/920   | 1000/1000 | 1500/1500 | 1700/1700 |
|  | MARV    | AS 3706.3     | N                     | 780/780   | 850/850   | 1250/1250 | 1440/1440 |
| CBR Puncture   | Typical | AS 3706.4     | N                     | 6800      | 8000      | 12000     | 15500     |
|  | MARV    | AS 3706.4     | N                     | 5800      | 6800      | 10000     | 13000     |
| Drop Cone  | Typical | AS 3706.5     | mm                    | 6         | 5         | 4         | 3         |
| HYDRAULIC PROPERTIES   |         |               |                       |           |           |           |           |
| Opening Size   | Typical | AS 3706.7     | Micron                | <75       | <75       | <75       | <75       |
| Flow Rate  | Typical | AS 3706.9     | L/m <sup>2</sup> /sec | 60        | 50        | 40        | 30        |
| RETAINED STRENGTH (Ultraviolet Radiation): When tested in accordance with AS 3706.11, shall have retained strength of at least 50% |         |               |                       |           |           |           |           |

**DISCLAIMER:** The information provided in this publication is correct to the best knowledge of the company and is given out in good faith. The information presented herein is intended only as a general guide to the use of such products and no liability is accepted by Cirtex Industries Ltd for any loss or damage however arising, which results either directly or indirectly from the use of such information. Cirtex Industries Ltd has a policy of continuous development so information and product specifications may change without notice.

This product has been manufactured under the controls established by a Bureau Veritas certification approved management system that conforms with ISO 9001:2015. Bureau Veritas Certification certificate number NZ001832-2

