

FILTERSLEEVE™

FILTER FABRIC

TECHNICAL DATA SHEET	TDS G 001 030
ISSUE NUMBER	05
DATE	MARCH 2020

TESTED AND APPROVED TO RMS SPECIFICATION 3553	
RMS T1520 - Determination of yield of a Seamless Tubular Filter Fabric	
Determination of Yield (m/kg)	30.472
Longitudinal Strain (%)	4.65
RMS T1521 - Laddering, Unraveling, or Deweaving of a Seamless Knitted Tubular Filter Fabric from a Cut End	
Laddering (from cut end)	Pass
Unraveling (from a cut end)	Pass
Deweaving (from a cut end)	Pass
RMS T1522 - Abrasion Resistance of Seamless Knitted Tubular Filter Fabric	
Holing	Pass
Unraveling	Pass
Laddering	Pass
Deweaving	Pass
RMS T1523 - Weave Stability of Seamless Knitted Tubular Filter Fabric	
Holing	Pass
Unraveling	Pass
Laddering	Pass
Deweaving	Pass
RMS T1524 - Determination of Opening Size of Seamless Knitted Tubular Filter Fabric	
Representative Large Opening Diameter (µm)	325
Opening Index	165
Range of Diameters - based on 10 largest diameters	
Photograph	Range (um)
1	215-345
2	323-352
3	232-315
Flow Rate (100mm Constant Head)	959 litres/sec/m ²
Permittivity (per single layer)	9.59 sec ⁻¹
Material	Polyester
Construction	Knitted

Standard installation drawings area available for subsoil drains on request

DISCLAIMER

The information provided in this publication is correct to the best knowledge of the company and is given out in good faith. The information presented herein is intended only as a general guide to the use of such products and no liability is accepted by Cirtex Industries Ltd for any loss or damage however arising, which results either directly or indirectly from the use of such information. Cirtex Industries Ltd has a policy of continuous development so information and product specifications may change without notice.



ISO 9001:2015
Registration number: C41186