

DURAMAT RF

Reinforced Turf Reinforcement Matting Zn Al PVC

TECHNICAL DATASHEET	G 080 002
ISSUE NUMBER	05
DATE	APRIL 2022

DESCRIPTION

DuraMat is a three dimensional high void ratio polypropylene geomat obtained from extruded monofilaments, tangled and welded where they cross. The geomat is bonded during the production process with a double twist metal mesh.

PROPERTIES	STANDARD	UNIT	VALUE
REINFORCEMENT PROPERTIES			
Raw Materials			Hexagonal double twist mesh with PVC coating
Protection of Metallic Wire			Galfan, Zn-Al alloy 5%
Properties of Protection of Metallic Wire	EN 10244-2		Class A
Content of Protection of Metallic Wire		gr/m²	≥230
Mesh Type		mm	60 x 80
Wire Thickness	EN 10218	mm	2.2 uncoated / 3.2 coated
Plastic Coating Thickness		mm	0.5
Outwearing Accelerated Aging test in SO2 (28 cycles)	EN ISO 6988	Pass	
Durability Double Twist Mesh	EN 10223-3 Annex A Table AI 1-3	Years	120 years
Jointing	Jointing of Cirtex DuraMat RF shall be performed with either high tensile Stainless Steel 3mm hog rings or continuous 2.2mm Galv + PVC coated lacing wire.		
GEOMAT PROPERTIES			
Application			Erosion Control
Raw Material			Polypropylene
PHYSICAL CHARACTERISTICS			
Geomat Weight	EN 9864	g/m²	800 (tol+/-5%)
Total Thickness	EN 9863-1	mm	10 (tol+3mm)
Tensile Strength MD (Machine Direction)		kN/m	>37
Void Ratio		%	>95
Roll Dimensions		m	2 x 25

The listed technical values are guiding values, achieved in our laboratories and/or independent testing institutes. Our products are subject to changes without prior notice.

DISCLAIMER

All information provided in this document is correct to the best knowledge Cirtex Industries Pty Ltd ("Cirtex") and is given out in good faith. While every effort has been made to ensure the accuracy of the information in this catalogue, Cirtex assumes no responsibility for errors or omissions or for any consequences of reliance on this catalogue. The information presented herein is intended only as a general guide to the use of such products and no responsibility or liability is accepted by Cirtex for any loss or damage however arising, which results either directly or indirectly from use of such information. Cirtex has a policy of continuous development therefore information and product specifications may change without notice. This document is subject to copyright in its entirety. The contents may not be reproduced in any form, either in whole or in part, without written permission from Cirtex. Copyright 2021. All rights reserved.



This product has been manufactured under the controls established by Bureau Veritas certification approved management system that conforms with ISO 9001:2015. Bureau Veritas Certification certificate number NZ 001784-1