



CIRTEX®
GAIN MORE GROUND™

MAGNUMSTONE™ SPECIFICATIONS

Gravity Segmental Retaining Wall

FORM NUMBER: G 128 005
ISSUE NUMBER: 01
REVISION DATE: SEPTEMBER 2021



1800 012 681 | WWW.CIRTEX.COM.AU



SPECIFICATIONS FOR MAGNUMSTONE™

Gravity Segmental Retaining Wall System

Part 1 General

1.01 SCOPE OF WORK

- A. Furnish all labor, materials, equipment, and incidentals required to install a precast concrete gravity Segmental Retaining Wall (SRW) with MagnumStone™ units as specified in the construction drawings or as established by the Owner, Architect or Engineer.

1.02 REFERENCE STANDARDS

- A. Engineering Design
 - 1. State Government regulations including TfNSW Specification R63 Geotextiles and TMR Specification MRTS27 Geotextiles
 - 2. AASHTO Standard Specifications for Highway Bridges
 - 3. TfNSW Specification R57 Design of Reinforced Soil Walls and TMR MRTS06 Reinforced Soil Structures
 - 4. NCMA Design Manual for Segmental Retaining Walls (SRW)
 - 5. ASTM D6916-03, Standard Test Method for Determining the Shear Strength Between Segmental Concrete Units (Modular Concrete Blocks)
- B. Segmental Retaining Wall (SRW) units
 - 1. AS 4455.1 Masonry units, pavers, flags and segmental retaining wall units Masonry units
 - 2. AS/NZS 4456.4-2003 Masonry units and segmental pavers and flags - Methods of test - Determining compressive strength of masonry units
- C. Soils
 - 1. AS 1289.5.1.1:2017 Methods of testing soils for engineering purposes Soil compaction and density tests—Determination of the dry density/moisture content relation of a soil using standard compactive effort
 - 2. AS 1289.2.1.1-2005 Methods of testing

soils for engineering purposes Soil moisture content tests - Determination of the moisture content of a soil - Oven drying method (standard method)

- 3. AS 1289.5.4.2-2007 Methods of testing soils for engineering purposes Soil compaction and density tests - Compaction control test - Assignment of maximum dry density and optimum moisture content values
- 4. ASTM D 2487 Standard Classification of Soils (Unified Soil Classification System)

D. Drainage Pipe

- 1. AS/NZS 2032:2006 Installation of PVC pipe systems
- 2. AS 2439.1—2007 Perforated plastics drainage and effluent pipe and fittings

- E. The Owner or Owner's Representative shall determine the final application, if the specifications and reference documents conflict.

1.03 DESIGN SUBMITTALS

- A. Material installation and description data shall be submitted for each product specified.
- B. SRW designs and drawings shall be submitted and include: bottom and top of wall elevation; drainage details; retaining wall layout with wall lengths, curve radii, and corner angles; typical wall sections; reference distances from fixed points; and any other unique application information.
- C. Design Methods and Calculations in accordance with either/or NCMA Design Manual 3rd edition, TfNSW Specification R57 Design of Reinforced Soil Walls or TMR MRTS06 Reinforced Soil Structures shall be submitted. Global stability analyses shall be calculated and submitted as part of the final design.
- D. Samples of the SRW units, color, and



texture shall be submitted, as per design specifications.

- E. Test reports in accordance with AS/NZS 4456.4-2003 and performed by an accredited laboratory shall be submitted.
- F. All submittals shall be provided, reviewed, and approved prior to the start of retaining wall construction.

1.04 RETAINING WALL DESIGN STANDARDS

- A. The wall design engineer and/or geotechnical engineer shall consider the internal stability, local stability, external stability, bearing capacity, and global stability of the soil mass above, behind and below the wall structure.
- B. The MagnumStone™ wall system shall be designed in accordance with the NCMA Design Manual for Segmental Retaining Walls, Third Edition or in accordance with TfNSW Specification R57 Design of Reinforced Soil Walls or TMR MRTS06 Reinforced Soil Structures. The minimum factors of safety shall be (or greater if specified by the engineer):
 - 1. External Stability: Base Sliding = 1.5; Overturning = 2.0; Bearing Capacity = 2.0; Global Stability = 1.3
 - 2. Internal Stability: Tensile Overstress = 1.5; Pullout = 1.5; Internal Sliding = 1.5
 - 3. Local Stability: Facing Shear = 1.5; Connection = 1.5
- C. Soil parameters for design must be selected by a suitably qualified geologist or geotechnical engineer and approved by the design engineer.
- D. The site grades and information shall determine the length, height, and overall elevations for the MagnumStone™ retaining wall requirements.
- E. The design height (H) shall be measured from the top of the base leveling pad to the top of the wall cap units.
- F. The above and below slopes of the wall details shall be depicted on the site construction drawings.
- G. The minimum embedment depth of the wall shall be no less than 1/2 unit 0.3 m or H/10 or as specified by the site construction drawings.
- H. The wall design must be approved by a Chartered Professional Engineer before construction starts.

1.05 DELIVERY, STORAGE, AND HANDLING

- A. The Contractor shall inspect all materials delivered to the site to ensure proper type

and grade of materials have been received as per the project specifications.

- B. The Contractor shall ensure proper storage, handling, and protection from damage of the materials. Damaged materials shall not be used in the construction of the Segmental Retaining Wall.
- C. The Contractor shall prevent excessive mud, wet concrete, or materials that may stain or adhere from coming in contact with the wall materials.

1.06 QUALITY ASSURANCE

- A. Contractor and Site Supervisor shall have proven qualified experience to complete the installation of the segmental retaining wall system.
- B. Retaining wall design engineer shall have proven qualified experience in performing all retaining wall analysis calculations.
- C. The owner is responsible to engage testing and inspection services to provide independent quality construction assurance.
- D. Independent inspection professionals shall ensure that all parameters and construction specifications have been followed in accordance to the design drawings and specifications.

1.07 QUALITY CONTROL

- A. The wall project installer is responsible to ensure that all installation and materials meet the quality specified in the construction drawings.
- B. A qualified independent party shall be responsible to verify that installation procedures have been installed in accordance with the specifications and construction drawings.
- C. All site construction tolerances for vertical alignment, horizontal locations for elevations, corner and radius locations, wall batter, and minimum bulging will be within NCMA and/or AASHTO specifications.

1.08 PAYMENT

- A. Payment for the installation of the MagnumStone™ wall shall be based on the unit price per square face foot (or square face meter) of wall product installed. The shipping and delivery slips shall be verified by both Contractor and Owner, or Owner's representative, at the time of product delivery to the site; this will be the basis of the final count or product used.

Part 2 Materials

2.01 CONCRETE SEGMENTAL RETAINING WALL (SRW) UNITS

- A. SRW concrete units shall be MagnumStone™ units as manufactured by Cirtex Industries Ltd
- B. MagnumStone™ units shall have a minimum 28 days compressive of equal to 30 MPa
- C. Color for the MagnumStone™ units shall be natural unless specified otherwise.
- D. The height dimensions shall not vary more than ± 3 mm from front to back and ± 6 mm from end to end, over 1.2m.
- E. The MagnumStone™ standard units shall have a face area of 0.75m² and MagnumStone™ half high units shall have a face area of 0.375m²
- F. The MagnumStone™ Standard unit weight shall approximately ± 615 kg with a gravel infill weight of ± 305 kg.
- G. The MagnumStone™ units shall be sound and free of cracks, chips or other defects that may prevent the contractor from properly installing the wall units or reduce the long-term strength of the wall structure.
- H. Concrete sampling and compression testing shall be in accordance with AS 4455.1 and AS/NZS 4456.4-2003.
- I. Reinforcing mesh (if required) shall be fabricated according to specific engineering design.
- J. Electrochemical requirements, if applicable, will follow AASHTO specifications.

2.02 FOUNDATION SOIL

- A. The foundation soils shall be undisturbed native site soils or as approved by the geotechnical engineer.
- B. The foundation soils shall be inspected and tested by an engineer before installing base leveling gravel.
- C. Disturbed or unsuitable foundation soils shall be properly compacted or replaced with acceptable soils as specified by the engineer.

2.03 BACKFILL SOIL

- A. Backfill soils shall be free of organic materials and other unsuitable materials.
- B. Soils classified as GP, GW, SP, SW, or SM types in accordance with ASTM D 2487 are likely to be suitable subject to approval by the design engineer.
- C. The Plasticity Index of the backfill soils shall be less than 20.

2.04 BASE LEVELING MATERIALS

- A. The base leveling gravel shall be well graded compacted gravel (GW).
- B. Unreinforced concrete base leveling pad can also be used if specified.

2.05 DRAINAGE AND UNIT INFILL AGGREGATE

- A. Drainage Aggregate shall be 20/40 clean crushed angular material or similar approved with particle size no less than 20 mm.
- B. Drainage Aggregates shall be placed in all unit voids and wedge between units, and between extenders.
- C. Unit weight of drainage aggregate must be as specified in the design.

2.06 DRAINAGE PIPE

- A. Drainage pipe shall be perforated PVC or corrugated HDPE pipe with a minimum size 0.1 m in diameter.
- B. Geotextile wrap around the drainage pipe may be used as specified by the engineer.
- C. Subsoil drainage system must be designed to the relevant authority guidelines and site specific design requirements.

2.07 GEOTEXTILE FABRIC

- A. Geotextiles shall be non-woven as specified by the specifications and construction drawings.
- B. Geotextiles when used as a soil separator shall be permeable, allowing water to effectively pass through the fabric openings.

Part 3 Execution

3.01 EXCAVATION

- A. The Contractor shall excavate to the lines and grades shown on the project grading plans.
- B. Back excavation cuts shall be notched benches of 1.5 m vertical for every 0.6 m horizontal bench, or as per the engineer's specifications.
- C. Over-excavated or filled areas shall be well compacted and inspected by an engineer.
- D. Excavated materials that are used for the backfilling reinforcement zone shall be protected from weather.
- E. Organic or other non-gravel materials shall not be used in the backfilled reinforcement zone.



3.02 FOUNDATION PREPARATION

- A. The foundation trench shall be excavated to the dimensions indicated on the construction drawings.
- B. The reinforced zone and leveling pad foundation soil shall be examined by the on-site engineer to ensure proper bearing strength.
- C. Soils not meeting the required strength shall be removed and replaced with proper materials.
- D. Foundation materials shall be compacted to a minimum of 95% Standard Proctor dry density, or greater, before placing leveling pad.

3.03 BASE LEVELING PAD

- A. Granular aggregate materials, minimum 0.15 m thick and width specified on the construction drawings, shall be placed and compacted to a minimum of 95% Standard Proctor dry density, or greater (an unreinforced concrete pad may be used).
- B. The base leveling pad shall be level horizontally and back to front to ensure the first course of units are level.
- C. The top of base leveling pad elevation and installation of granular materials shall be in accordance with the specifications and construction drawings. The toe of the wall burial depth shall be constructed as shown on the construction drawings.
- D. Where concrete reinforced footing is required, they shall be installed below the frost level and constructed in accordance with the specifications and construction drawings.

3.04 UNIT INSTALLATION

- A. The first course of MagnumStone™ units shall be carefully placed on a well-graded gravel or concrete leveling pad.
- B. The first row of units shall be level from unit to unit and from back to front.
- C. A string line can be used to align a straight wall. PVC flex pipes can be used to establish smooth convex or concave curved walls.
- D. The smooth back of the units shall be used for alignment and measuring to ensure smooth curves and straight walls.
- E. The second course of units shall have the concrete connecting lugs in the unit voids of the first course below, and pulled forward resting the lugs against the front edge of the two lower unit voids.

- F. All units shall be laid snugly together and parallel to the straight or curved lines.
- G. The MagnumStone™ units shall be swept clean of all dirt or rocks before installing the next layer of units or placing the geosynthetics.
- H. After laying each course, perform a visual or string line straightness check.

3.05 DRAINAGE COMPONENTS

- A. Drainage pipe and geotextile shall be installed as shown on the construction drawings.
- B. MagnumStone™ unit voids and the drainage chimney that is 0.15 to 0.3 m behind the wall shall be filled with a free-draining granular material, as specified in section 2.05 (clean gravel).
- C. Clean gravel shall be placed into the unit voids and behind the wall for each course.
- D. Clean gravel only requires light vibratory compaction.
- E. Drainage outfalls are to be as per construction drawing or as agreed by the engineer on site.

3.06 BACKFILL

- A. Reinforced backfill materials shall be placed in maximum lifts of 0.3 m and shall be compacted to a minimum 95% Standard Proctor density or greater to the lines and grades shown on the project grading plans.
- B. Only hand-operated compaction equipment shall be used within 0.6 m of the back of the wall.
- C. Soil density testing shall not be taken within this 0.6 m area.
- D. The toe of the wall shall be filled and compacted as the wall is being constructed.

3.07 CAP INSTALLATION

- A. The MagnumStone™ full size cap units shall be placed in the same installation procedures as the regular MagnumStone™ units.
- B. Geotextiles should be used as a soil separator between the final layer of drainage materials and the topsoil materials to prevent fines from migrating into the drainage gravel or through the wall face.
- C. A MagnumStone™ 0.15 m high cap can be used to complete the top of the wall. Concrete adhesive shall be used to glue the cap units to the regular units.

End of Section



DISCLAIMER

All information provided in this document is correct to the best knowledge Cirtex Industries Pty Ltd ("Cirtex") and is given out in good faith. While every effort has been made to ensure the accuracy of the information in this catalogue, Cirtex assumes no responsibility for errors or omissions or for any consequences of reliance on this catalogue. The information presented herein is intended only as a general guide to the use of such products and no responsibility or liability is accepted by Cirtex for any loss or damage however arising, which results either directly or indirectly from use of such information. Cirtex has a policy of continuous development therefore information and product specifications may change without notice. This document is subject to copyright in its entirety. The contents may not be reproduced in any form, either in whole or in part, without written permission from Cirtex. Copyright 2021. All rights reserved.

CIRTEX INDUSTRIES PTY LTD

Head Office 100 Silverwater Rd, Silverwater NSW 2128, Australia
Postal Address PO Box 7138, Silverwater NSW 1811, Australia

1800 012 681 | WWW.CIRTEX.COM.AU