

GEOTER F-PET

HIGH STRENGTH GEOTEXTILE

TECHNICAL DATA SHEET	G 100 002
ISSUE NUMBER	04
DATE	APRIL 2021

Geoter F-PET from Texinov is a composite geotextile made with high tenacity PET cables, manufactured by warp knitting process with weft and warp insertion, with a backing of woven PP geotextile to provide enhanced separation, filtration and protection characteristics. It is especially designed for reinforcement of embankments on soft soils, road foundations, and supporting structures, fills and slopes.

Tensile Strength MD (min value) can be verified with batch test data for every project

Tensile Strengths which fall between those listed may also be used with the appropriate reduction factors listed here calculated as follows

Tensile Strength MD / (RFCR*RFID*RFD) Contact Cirtex Industries Ltd to verify calculations 0800 247 839

PROPERTY	STANDARD	UNIT	F-PET 100/50	F-PET 200/50	F-PET 300/50	F-PET 400/50	F-PET 600/50	F-PET 800/50	F-PET 1000/100	F-PET 1350/135	F-PET 1600/100	F-PET 1800/100
Mechanical Properties												
Tensile Strength MD (min value)	ISO 10319	kN/m	100	200	300	400	600	800	1000	1350	1600	1800
Tensile Strength CD (min value)	ISO 10319	kN/m	50	50	50	50	50	50	100	135	100	100
Nominal strain at initial strength	ISO 10319	%	10	10	10	10	10	10	10	10	10	10
Reduction Factor CR - Creep Rupture @ 20° C												
10 year design life			1.4	1.4	1.4	1.4	1.4	1.4	1.4	1.4	1.4	1.4
50 year design life			1.45	1.45	1.45	1.45	1.45	1.45	1.45	1.45	1.45	1.45
100 year design life			1.47	1.47	1.47	1.47	1.47	1.47	1.47	1.47	1.47	1.47
Reduction Factor ID - Installation damage												
in Clay, Silt, Sand < 5mm			1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1
in Aggregates < 100mm			1.15	1.15	1.15	1.15	1.15	1.15	1.15	1.15	1.15	1.15
Reduction Factor D - Environmental Degradation pH 5 - 8												
for 10 year design life			1	1	1	1	1	1	1	1	1	1
for 50 year design life			1.05	1.05	1.05	1.05	1.05	1.05	1.05	1.05	1.05	1.05
for 100 year design life			1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1
Long Term Design Strength in Clay, Silt, Sand												
10 year design life			64.9	129.9	194.8	259.7	389.6	519.5	649.4	876.6	1039.0	1168.8
50 year design life			59.7	119.4	179.1	238.8	358.3	477.7	597.1	806.1	955.4	1074.8
100 year design life			56.2	112.4	168.7	224.9	337.3	449.8	562.2	759.0	899.5	1012.0
Long Term Design Strength in Aggregates < 100mm												
10 year design life			62.1	124.2	186.3	248.4	372.7	496.9	621.1	838.5	993.8	1118.0
50 year design life			57.1	114.2	171.3	228.5	342.7	456.9	571.1	771.0	913.8	1028.1
100 year design life			53.8	107.6	161.3	215.1	322.7	430.2	537.8	726.0	860.4	968.0

ISO 9001

BUREAU VERITAS
Certification



This product has been manufactured under the controls established by Bureau Veritas certification approved management system that conforms with ISO 9001:2015. Bureau Veritas Certification certificate number NZ 001784-1

DISCLAIMER

All information provided in this document is correct to the best knowledge Cirtex Industries Pty Ltd ("Cirtex") and is given out in good faith. While every effort has been made to ensure the accuracy of the information in this catalogue, Cirtex assumes no responsibility for errors or omissions or for any consequences of reliance on this catalogue. The information presented herein is intended only as a general guide to the use of such products and no responsibility or liability is accepted by Cirtex for any loss or damage however arising, which results either directly or indirectly from use of such information. Cirtex has a policy of continuous development therefore information and product specifications may change without notice. This document is subject to copyright in its entirety. The contents may not be reproduced in any form, either in whole or in part, without written permission from Cirtex. Copyright 2021. All rights reserved.



CIRTEX
GAIN MORE GROUND

1800 012 681 | WWW.CIRTEX.COM.AU