

DURAGRID X

PP GEOGRID

TECHNICAL DATA SHEET	G 032 001
ISSUE NUMBER	03
DATE	AUGUST 2023

DuraGrid X Geogrid is an integrally formed structure, which is especially designed for soil stabilisation and reinforcement applications. **DuraGrid X** is manufactured from polypropylene, from the process of extruding, longitudinal stretching and transverse stretching. **DuraGrid X** is manufactured in a facility that has achieved ISO9001 certification and has passed the CE certification.

Typical Applications include but are not limited to: subgrade and embankment stabilisation, vertical load distribution and base/slope reinforcement.

DuraGrid X conforms to the property values listed below.

PHYSICAL PROPERTIES	TEST METHOD	UNITS	DURAGRID X 20/20	DURAGRID X 30/30	DURAGRID X40/40
			MD/TD	MD/TD	MD/TD
APERTURE DIMENSIONS ± 4mm	Measured (Nominal)	mm	36/36	36/36	34/34
ULTIMATE TENSILE STRENGTH	ASTM D 6637	kN/m	20.0/20.0	30.0/30.0	40.0/40.0
TENSILE STRENGTH AT 2% STRAIN	ASTM D 6637	kN/m	7/7	10.5/10.5	14/14
TENSILE STRENGTH AT 5% STRAIN	ASTM D 6637	kN/m	14/14	21/21	28/28
RADIAL STIFFNESS AT 0.5%	Note 3	kN/m	390	580	760
JUNCTION STRENGTH	GRI GG2	%	93%	93%	93%
CARBON BLACK	ASTM D 4218	%	2	2	2
ROLL WIDTH x LENGTH	Measured	m	3.95 x 25	5.95 x 50	5.95 x 50

NOTES:

1. Cirtex Industries Ltd reserves the right to alter product specifications at any time without prior notice. It is the responsibility of all users to satisfy themselves that the above data is current and that the product is suitable for its intended end use.
2. Polypropylene is the constituent polymer used in the production of **DuraGrid X**.
3. Cirtex Industries Ltd uses internationally recognised test methods to measure radial stiffness, including ISO 10319/ASTM6637 Wide Width testing and DIN 61551 radial testing. Please contact our technical team for more information.

DISCLAIMER

All information provided in this document is correct to the best knowledge Cirtex Industries Pty Ltd ("Cirtex") and is given out in good faith. While every effort has been made to ensure the accuracy of the information in this catalogue, Cirtex assumes no responsibility for errors or omissions or for any consequences of reliance on this catalogue. The information presented herein is intended only as a general guide to the use of such products and no responsibility or liability is accepted by Cirtex for any loss or damage however arising, which results either directly or indirectly from use of such information. Cirtex has a policy of continuous development therefore information and product specifications may change without notice. This document is subject to copyright in its entirety. The contents may not be reproduced in any form, either in whole or in part, without written permission from Cirtex. Copyright 2021. All rights reserved.



This product has been manufactured under the controls established by Bureau Veritas certification approved management system that conforms with ISO 9001:2015. Bureau Veritas Certification certificate number NZ001832-2