

GridTex 20/20

COMPOSITE GEOGRID

TECHNICAL DATA SHEET	G 032 011
ISSUE NUMBER	03
DATE	OCTOBER 2019

Cirtex Composite Geogrids are geocomposites especially designed for soil stabilisation and reinforcement applications. Cirtex Composite Geogrids are manufactured by bonding a Biaxial Geogrid to a nonwoven polyester geotextile.

GEOGRID INDEX PROPERTIES	TEST METHOD	UNITS	MD VALUES	TD VALUES
POLYMER	-	-	PP	-
MINIMUM CARBON BLACK	ASTM D 4218	%	2	-
TENSILE STRENGTH @ 2% STRAIN	ASTM D-6637	kN/m	7	7
TENSILE STRENGTH @ 5% STRAIN	ASTM D-6637	kN/m	14	14
ULTIMATE TENSILE STRENGTH	ASTM D-6637	kN/m	20	20
RADIAL STIFFNESS @ 0.5%	NOTE 3	kN/m	390	
GEOTEXTILE PHYSICAL PROPERTIES				
POLYMER	-	-	PET	-
MASS PER UNIT AREA	ASTM D 5261	g/m ²	200	-
ULTIMATE TENSILE STRENGTH	ASTM D 4595	kN/m	14	12
TENSILE ENLONGATION	ASTM D 4595	%	50	50
CBR PUNCTURE STRENGTH	ASTM D 6241	N	2300	-
APPARENT OPENING SIZE	ASTM D 4751	mm	0.11	-
FLOW RATE	ASTM D 4491	l / m ² /s	220	-
DIMENSIONS		3.9m x 50m		

NOTES:

- Cirtex Industries Ltd reserves the right to alter product specifications at any time without prior notice. It is the responsibility of all users to satisfy themselves that the above data is current and that the product is suitable for its intended end use.
- Polypropylene is the constituent polymer used in the production of GridTex.
- Cirtex Industries Ltd uses internationally recognised test methods to measure radial stiffness, including ISO 10319/ASTM6637 Wide Width testing and DIN 61551 radial testing. Please contact our technical team for more information.

DISCLAIMER

All information provided in this document is correct to the best knowledge Cirtex Industries Pty Ltd ("Cirtex") and is given out in good faith. While every effort has been made to ensure the accuracy of the information in this catalogue, Cirtex assumes no responsibility for errors or omissions or for any consequences of reliance on this catalogue. The information presented herein is intended only as a general guide to the use of such products and no responsibility or liability is accepted by Cirtex for any loss or damage however arising, which results either directly or indirectly from use of such information. Cirtex has a policy of continuous development therefore information and product specifications may change without notice. This document is subject to copyright in its entirety. The contents may not be reproduced in any form, either in whole or in part, without written permission from Cirtex. Copyright 2021. All rights reserved.

ISO 9001

BUREAU VERITAS
Certification



This product has been manufactured under the controls established by Bureau Veritas certification approved management system that conforms with ISO 9001:2015. Bureau Veritas Certification certificate number NZ 001784-1